

Supplementary Material to the article "Tricarboxylic Acids and Ethylenediamine Derived Carbon Dots for Organic Light-Emitting Diodes"




Fig. S1. (a) Electroluminescence spectrum of the OLED structure ITO/PEDOT-PSS(50 nm)/poly-TPD(20 nm)/CA-2-CDs/TPBi(15 nm)/LiF(1 nm)/Al(50 nm). The additional bend in the band at 630 nm observed at 7 V is presumably attributed to electroluminescence from the transport layers, poly-TPD and/or TPBi, (b) I-V curve and brightness-voltage dependence of the OLED structure.